## The Copper Connection System Expansion/Contraction Accommodation

Copper tubing, as well as all piping matrials, expands and contracts with temperature changes. Therefore, in a copper tube system, the pipe line can buckle or bend when it expands unless compensation is built into the system. Harmful stresses, buckling and bending are prevented by installing expansion loops.

The following chart provides information on calculating the expansion/contraction of copper tubing due to thermal changes; and the accommodation of this movement with expansion loops constructed of Style 606 couplings and Number 610 Copper 90° Elbows.

Temperature °F/°C	Copper Inches/millimeters
-40	-0.421
-40	-10,69
-20	-0.210
-29	-5,33
0	0
-18	0
20	0.238
	6,05
32	0.366
0	9,30
40	0.451
4	11,46
60	0.684
16	17,37
80	0.896
2/	22,76
100	1.134
	28,80
120	1.366
49	34,70
140	1.590
00	40,39
160	1.804
//	45,82
180	2.051
02	32,10
200	2.290
212	2,420
212	2.428
	2 516
220	63.91
220	2.626
110	66,95

#### Expansion Loops for Joining Copper Tubing with Victaulic Copper Connection Products Expansion loops or "U" bends are frequently used to accommodate

Expansion loops or "U" bends are frequently used to accommodate the expansion and/or contraction of pipe lines due to thermal changes. Copper tube, as does all piping materials, expands and contracts with these temperature changes. The above table shows the actual expansion of 100' pipe lengths for copper pipe. Calculations for the anticipated expansion/contraction can be obtained from the example shown in 26.02. The necessary length of the copper tube expansion loop can be calculated from the following formula:

$$L = \sqrt{\frac{3EDe}{S}} \qquad (1)$$

L = Loop length, in inches, as shown in the figures below:



E = modulus of elasticity of copper in PSI = 15,600,000 PSI S = allowable stress of material in flexure, in PSI = 6000 PSI D = outside diameter of copper tubing in inches e = amount of expansion to be absorbed, in inches Simplifying the formula:

$$L = 88.32\sqrt{De} \quad (2)$$

Calculated Loop lengths for various expansions are shown in the table below:

Expansion Inches mm	Loop Length "L" for Tube Sizes Shown Inches/millimeters						
	2½ 73,0	3 88,9	4 114,3	5 141,3	6 168,3	8 219,1	
1/ <sub>2</sub>	102	111	127	142	155	178	
12,7	2591	2819	3226	3607	3937	4522	
1	144	157	180	200	219	252	
25,4	3658	3988	4572	5080	5563	6401	
1 <sup>1</sup> / <sub>2</sub>	176	192	220	245	268	309	
38,1	4470	4877	5588	6223	6807	7849	
2	203	221	254	283	310	356	
50,8	5156	5613	6452	7188	7874	9043	
2 <sup>1</sup> / <sub>2</sub>	227	247	284	317	346	398	
63,5	5766	6274	7214	8052	8788	10109	
3	248	271	311	347	379	436	
76,2	6299	6883	7899	8814	9627	11074	

Note: Expansion Loop should be located between two anchors and the pipe should be guided so as to direct the movement into the loop.

#### References:

(1)Copper/Brass/Bronze Product Handbook, Copper Development Association, Inc.

(2)Source Book on Copper and Copper Alloys.

American Society for Metals

The data provided is intended for use as an aid to qualified designers when products are installed in accordance with the latest available Victaulic product data.

® REGISTERED TRADEMARK OF VICTAULIC - © COPYRIGHT 1997 VICTAULIC - PRINTED IN U.S.A.

Victaulic Company of America • Phone: 1-800-PICK-VIC (1-800-742-5842) • Fax: 610-250-8817 • e-mail:pickvic@victaulic.com Victaulic Company of Canada • Phone: 905-884-7444 • Fax: 905-884-9774 • e-mail: viccanada@victaulic.com Victaulic Europe • Phone:32-9-381-1500 • Fax: 32-9-380-4438 • e-mail: viceuro@victaulic.be Victaulic America Latina • Phone: 610-559-3300 • Fax: 610-559-3608 • e-mail: vica@victaulic.com Victaulic Asia Pacific • Phone: 65-6235-3035 • Fax: 65-6235-0535 • e-mail: vicag@victaulic.com



VICTAULIC® IS AN ISO 9001 CERTIFIED COMPANY

### Support

The requirements of MSS-SP-69 "Pipe Hangers and Supports – Selection and Application" shall, in general, govern the installation of hangers and supports, in accordance with the following recommendations: Copper tubing joined with grooved type couplings requires support to carry the weight of tubing and equipment. The support or hanging method must be such as to eliminate undue stresses on joints, tubing and other components. Additionally, the method must be such as to allow movement of tubes where required and to provide for other special requirements such as drainage, etc., as may be required by the designer. The support system for mechanical grooved type tubing couplings must consider some of the special requirements of these couplings.

The table shows suggested maximum span between supports for horizontal straight runs of copper tubing carrying water or similar liquids. These DO NOT apply where critical calculations are made or where there are concentrated loads between supports.

# SUGGESTED MAXIMUM SPAN BETWEEN SUPPORT FOR COPPER TUBING

TUBE SIZE Nominal Inches Actual mm	Water Service Feet/meters	Gas & Air Service Feet/meters
2	8	10
60,3	2,44	3,05
21/2	10	11
73,0	3,05	3,35
3	10	12
88,9	3,05	3,66
4	12	14
114,3	3,66	4,27
5	13	15
141,3	3,96	4,57
6	15	17
168,3	4,57	5,18
8	15	17
219,1	4,57	5,18

Spacing corresponds to ANSI B31.9 Building Services Code.